



**Preparation and characterization of silver nanoparticles prepared by floral aqueous extract of plant *Alstonia scholaris* Linn. R. Br. By Green synthesis approach.**

**Saurabh Sharma<sup>1</sup> and Dr. Swapnil Goyal<sup>2</sup>**

1. Ph.D Research Scholar, Faculty of Pharmacy, Mandsaur University, Mandsaur (M.P.) India, Email address: medilabujn@gmail.com, Mobile No. 8319097294.
2. Professor, Faculty of Pharmacy, Mandsaur University, Mandsaur (M.P.) India, Email address: swapnilmip@gmail.com, Mobile No. 9907860790.

---

**Abstract**

In recent times the fast and rapid research innovation done in the field of the Herbal Drug Industry as well as nanosciences and nanotechnology. They open the different doors of research related to the field of diagnosis, treatment, cure, and prevention of several diseases etc. Herbal-based formulation containing nano-range particles shows good effectiveness and better bioavailability in systemic circulations recorded their several advantages. Plant-based phytoconstituents are potential agents used for the synthesis of silver nanoparticles. Green synthesis-based inorganic silver nanoparticles are a fresh and promising alternative to chemically produced nanoparticles.

In this study green synthesis of silver nanoparticles using aqueous floral extract of *Alstonia scholaris* Linn. R. Br. UV-Vis spectrometer uses to monitor the reduction of Ag ions and the formation of silver nanoparticles with the plant extract. Particle size distribution TEM and FE-SEM have been used to investigate the morphology characters of prepared silver nanoparticles. FT-IR was performed to measure the different functional groups present in the nanoparticles. The peaks in the XRD pattern are associated with that of the face-centered-cubic (FCC) form of metallic silver. The average grain size of silver nanoparticles is found to be 6.45 nm.

**Keywords:** Green synthesis, Silver nanoparticles, *Alstonia scholaris*, Aqueous floral extract.

---

**1. Introduction**

Nanoparticles are the smallest size particles they have remarkably different properties and activities. Nanotechnology is the newer technology in which we are using small particle size (10-100 nm), shape, and quite unique in nature solid colloidal particles of the materials. It is widely used in different fields because of its various good advantages and applications<sup>[1-4]</sup>

They are classified and categorized in many ways, but application-based classification is very important for the classification of Nanoparticles. Organic and inorganic nature-based classification has easily differentiated the Nanoparticles. The different types of metallic Nanoparticles are widely used in past and recent times eg. Gold, Silver, Copper, Iron, Zinc, etc. Silver nanoparticles show good antimicrobial characteristics, and at present, their several applications are being explored in consumer products such as medicines, shampoo, hygiene products, and contraceptives<sup>[5-10]</sup>.

*Alstonia scholaris* Linn. R. Br. Plant is a large evergreen garden tree, belonging to the family Apocynaceae. It is growing up to 15–21 m in height, with a straight often. They contain different types of important alkaloids and other secondary metabolites. These substances are responsible for showing different types of medicinal properties. The ethno medicinal datashows that all the parts of the plant are used for medicinal purposes Bark, Leaves, Flower, latex, etc <sup>[11-13]</sup>.

In the present study we prepared silver nanoparticles using the aqueous floral extract of *Alstonia scholaris* by green synthesis approach and their optimization and characterization.

## 2. Material and Method

### 2.1 Chemicals

All chemicals used by Merck Pvt. Ltd. and solvents were Qualigens.

### 2.2 Plant material

Flowers are collected from the medicinal garden of Vikram University campus Ujjain (Voucher specimen MIPS- AS-001) according to session and shaded dry. Dry flowers are grinded using a mechanical mixer and formed a coarse powder.

### 2.3 Successive solvent extraction method <sup>[14]</sup>

Take coarsely powdered flower (40 g) were extracted by Soxhlet using non-polar to polar solvents (300 ml). Then, after extraction, solvents were removed by Rotavapor (Buchi, England) and a solid mass of aqueous extracts was procured.

### 2.4 Green synthesis of silver nanoparticle using *Alstonia scholaris* flower aqueous extract

In the green synthesis of silver nanoparticles firstly take 0.01M of an aqueous solution of silver nitrate(99.99%) was used. 10 mL of Floral aqueous extract was added to 100 ml of 0.01M silver nitrate aqueous solution and allowed at the ambient condition to react. After different time intervals, the colour change of the reaction mixture is observed from transparent yellow to dark brown indicates that the formation of silver nanoparticles. The silver nanoparticles solution was collected and UV-vis spectral analysis was used to investigate the reduction mechanism of silver ions into nanoparticles in the solution. The silver nanoparticles solution was allowed to centrifuge and the excess liquid was removed by evaporation in a dryer yielding black brown coloured silver nano powder <sup>[15-17]</sup>.

#### 2.4.1 Optimization of parameters for the synthesis of silver nanoparticles <sup>[18]</sup>

Optimization of external factors is critical to control reaction parameters. UV–vis analysis was done to obtain the optimum wavelength for silver nanoparticles.

#### 2.4.2 Optimization of pH for the formation of silver Nanoparticles <sup>[19]</sup>

pH was varied from 5 to 9 with a difference of 1 to estimate the optimal pH of silver nanoparticles.

### 2.5. Characterization of Silver Nanoparticles <sup>[20]</sup>

#### 2.5.1. Spectroscopical analysis

UV visible spectroscopy was performed on the aqueous floral extract of *Alstonia scholaris*-based silver nanoparticles with suitable dilutions to analyze absorbance and  $\lambda_{\text{max}}$  by Shimadzu 1800 (Shimadzu Corporation, Kyoto, Japan), and the spectra were taken <sup>[21]</sup>.

### 2.5.2. FTIR analysis

FT-IR studies of silver nanoparticles were done with an FT-IR spectrometer (Aligent Cary 630) from Diya Lab Mumbai using the dried powders between 4000–700  $\text{cm}^{-1}$  by means of KBr pellet method<sup>[22]</sup>.

### 2.5.3. Particle size analyser by Malvern<sup>[23]</sup>

Dynamic Light Scattering measures the translational diffusion coefficient of particles that are subject to Brownian motion by analyzing the intensity fluctuations of laser light scattered by the particles. The particle hydrodynamic size is then determined by modeling the particles as perfect solid spheres and applying the Mie and Rayleigh scattering theories.

### 2.5.4. FE Scanning electron microscopy

Silver nanoparticles were allowed to dry in a vacuum. Morphological analysis was done by Carl Zeiss, Model Supra 55 (Made in England)<sup>[24]</sup>.

### 2.5.5. Transmission electron microscopy (TEM)

The size of the nanoparticles was calculated by transmission electron microscopy (Tecnai T20, 200 Kev FEI instrument) from Sprint Testing Solutions Mumbai. Silver nanoparticles were loaded on TEM grids and kept in desiccators and transferred onto a specimen holder. The particle size of silver nanoparticles was estimated using Image J 1.45 s software (NIH, USA)<sup>[25]</sup>.

### 2.5.6 X-ray diffraction study (XRD)<sup>[26]</sup>

silver nanoparticles were characterized by XRD (Panalytical B.V. Lelyweg 1 7602 EA ALMELO The Netherland).

## 3. Results

The aqueous floral extract of silver nanoparticles was dark brown in color (Fig. 1) nanopowder was stable. The optimum concentration of *Alstonia scholaris* Linn for nanoparticle synthesis was 10 mL of Floral aqueous extract added to 100 ml of 0.01M silver nitrate aqueous solution. It was observed that acidic pH (3–5) was inhibiting synthesis for silver nanoparticles. A highly basic pH was optimum for the synthesis of green synthesis-based silver nanoparticles. In earlier studies, it was established that alkaline pH is favourable for the synthesis of silver nanoparticles

### 3.1 UV–vis analysis

UV visible spectroscopy spectra of the aqueous floral extract of *Alstonia scholaris*-based silver nanoparticles with suitable dilutions. The intensity of the absorption peak at 425 nm is recorded. (Fig. 1) shows spectra of aqueous floral extract of *Alstonia scholaris*-based silver nanoparticles. UV range from 200 to 700 nm and Millipore water was used as a blank to adjust the baseline.

### 3.2. FT-IR analysis

FT-IR spectra show different frequency ranges between 3600-3200  $\text{cm}^{-1}$  representing a hydroxyl (–OH) group peak report at 3365.8. (C-H) stretching from 2950-2840 peak report at 2922.2, (N-H) Primary Amines 1650-1550 peak report at 1561.8, and carbonyl (C=O) stretching of at (1275-1200) peak report at 1282.2, (Fig. 2)

### 3.3 Particle size

Silver nanoparticles Dynamic Light Scattering size measurements were performed on a Zetasizer Nano (Malvern Panalytical Ltd., UK) equipped with a maximum 4 mW He–Ne laser

emitting at 633 nm and Zetasizer Software, v. 7.13. Samples were contained in ZEN0040 (Malvern Panalytical) low volume disposable cuvettes. Each measurement was performed at a noninvasive back-scattering angle of  $173^\circ$  (in the dispersant) after thermally equilibrating the sample at  $25^\circ\text{C}$  for 3 min. (Fig.3)

### 3.4 FE-SEM

The reflected secondary electrons are captured by detectors converted into image. In this, among all the microscopy techniques, SEM is most efficient method for the measurement of nano level and identified easily different particle size and shapes of nanoparticles. It can also determine the basic information about surface the morphology of nanoparticles in nanoscale. Fig.4 (A–B) illustrates the FESEM studies of Silver Nanoparticles.

### 3.5 TEM

Transmission electron microscopy (TEM) is an important method of characterizing nanoparticle morphology (size and shape) (Stensberg et al., 2011) [(Warheit, 2010) (Sadik et al., 2009) 91,95]. TEM images of NPs are typically acquired in brightfield mode, based on the contrast generated by electron scattering from heavy atoms. The different image analysis software to obtain statistical distributions in particle size and shape. Individual NPs can also be assessed for uniformity in shape or size. TEM study shows measured Minimum particle size for AgNP-AS of 10 nm. Fig 5 (A-E).

### 3.6 X-ray diffraction studies

X-ray diffraction pattern of AgNP-AS had Bragg's reflections of (111), (200), (220) and (311) planes, which confirms the face-centered cubic (FCC) crystalline structure of silver (Fig. 6).

synthesized AgNPs using *Coriandrum sativum* leaf extract was shown in Fig. 4. The XRD was done to determine the crystalline nature of AgNPs and the resulted peaks were found at  $37.90^\circ$ ,  $44.05^\circ$ ,  $64.25^\circ$  and  $77.20^\circ$  representing (111), (200), (220) and (311) face centered cubic structure of silver which were compared with the standard powder diffraction card of Joint Committee on Powder Diffraction Standards (JCPDS), silver file No. 04–0783. A few intense unassigned peaks were also noticed which was raised at 320 , 45.950 , 54.60 and 57.20 . t .

## 4. Conclusion

The green synthesis-based method of AgNPs using aqueous floral extract of *Alstonia scholaris* was shown to be fast, eco-friendly, and cheaply produced nanoparticles that are in nano size and shape. Silver nanoparticles began to form within the addition of leaf extract to silver nitrate as shown by the UV-vis spectrum at 425 nm. The XRD peaks are ascribed with the FCC structure of silver. The synthesized Silver nanoparticles were spherical in shape and particle size was found about 6.45 nm from XRD results in addition justified further by the SEM. The FT-IR spectrum ascribed the biological molecules which perform dual functions of formation and stabilization of silver nanoparticles in the aqueous medium. So, it can be summarized that, green synthesis is an effective and eco-friendly method of producing metal nanoparticles.

### Declaration of Competing Interest

The authors report no declaration of interest.

### Acknowledgment

The study was undertaken from the funds of Department of Science and Technology (Ref:607(Sanc)/ST/P/S&T/5G-3/2016 dated 17/10/ 2016).

Fig. 1. UV-visible spectra of silver nanoparticles prepared by *Alstonia scholaris* Linn aqueous floral extract.




Fig. 2. FT-IR analysis of silver nanoparticles prepared by *Alstonia scholaris* Linn aqueous floral extract.




Fig. 3. Particle size distribution report graph of silver nanoparticles prepared by *Alstonia scholaris* Linn aqueous floral extract.



Fig. 4. FE-Scanning electron microscopy images of silver nanoparticles prepared by *Alstonia scholaris* Linn aqueous floral extract.

A. Image

B. Image







Fig. 5. FE- Scanning electron microscopy images of silver nanoparticles prepared by *Alstonia scholaris* Linn aqueous floral extract.

A. Image

B. Image

C. Image



D. Image

E. Image







Fig. 5. X-Ray diffraction of silver nanoparticles prepared by *Alstonia scholaris* Linn aqueous floral extract.



## Reference

1. Balaji DS, Basavaraja S, Deshpande R, Mahesh DB, Prabhakar BK, Venkataraman A. Extracellular biosynthesis of functionalized silver nanoparticles by strains of *Cladosporium cladosporioides* fungus. *Colloids and surfaces B: biointerfaces*. 2009 Jan 1;68(1):88-92.
2. Sirelkhatim A, Mahmud S, Seeni A, Kaus NH, Ann LC, Bakhori SK, Hasan H, Mohamad D. Review on zinc oxide nanoparticles: antibacterial activity and toxicity mechanism. *Nano-micro letters*. 2015 Jul;7:219-42.
3. Xu C, Qu X. Cerium oxide nanoparticle: a remarkably versatile rare earth nanomaterial for biological applications. *NPG Asia materials*. 2014 Mar;6(3):e90-.
4. Whitesides GM. Nanoscience, nanotechnology, and chemistry. *Small*. 2005 Feb;1(2):172-9.
5. Jaffri SB, Ahmad KS. Augmented photocatalytic, antibacterial and antifungal activity of prunosynthetic silver nanoparticles. *Artificial cells, nanomedicine, and biotechnology*. 2018 Oct 31;46(sup1):127-37.
6. Elahi N, Rizwan M. Progress and prospects of magnetic iron oxide nanoparticles in biomedical applications: A review. *Artificial Organs*. 2021 Nov;45(11):1272-99.
7. Bharathala S, Sharma P. Biomedical applications of nanoparticles. In *Nanotechnology in modern animal biotechnology* 2019 Jan 1 (pp. 113-132). Elsevier.

8. Flejszar M, Chmielarz P. Surface-initiated atom transfer radical polymerization for the preparation of well-defined organic–inorganic hybrid nanomaterials. *Materials*. 2019 Sep 18;12(18):3030.
9. Lizundia E, Puglia D, Nguyen TD, Armentano I. Cellulose nanocrystal based multifunctional nanohybrids. *Progress in Materials Science*. 2020 Jul 1;112:100668.
10. Khandel P, Yadaw RK, Soni DK, Kanwar L, Shahi SK. Biogenesis of metal nanoparticles and their pharmacological applications: present status and application prospects. *Journal of Nanostructure in Chemistry*. 2018 Sep;8:217-54.
11. Ghosh R, Sarkhel S, Saha K, Parua P, Chatterjee U, Mana K. Synthesis, characterization & evaluation of venom neutralization potential of silver nanoparticles mediated *Alstonia scholaris* Linn bark extract. *Toxicology Reports*. 2021 Jan 1;8:888-95.
12. Hembram KC, Kumar R, Kandha L, Parhi PK, Kundu CN, Bindhani BK. Therapeutic prospective of plant-induced silver nanoparticles: application as antimicrobial and anticancer agent. *Artificial cells, nanomedicine, and biotechnology*. 2018 Nov 12;46(sup3):38-51.
13. Kaushik P, Kaushik D, Sharma N, Rana A. *Alstonia scholaris*: It's Phytochemistry and pharmacology. *Chronicles of young scientists*. 2011 Apr 1;2(2):71-.
14. Mukherjee C, Suryawanshi PG, Kalita MC, Deka D, Aranda DA, Goud VV. Polarity-wise successive solvent extraction of *Scenedesmus obliquus* biomass and characterization of the crude extracts for broad-spectrum antibacterial activity. *Biomass Conversion and Biorefinery*. 2022 Feb 11:1-7.
15. Vindhya PS, Sajan D. Green Synthesis and Characterization of Silver Nanoparticles. *In Methodologies and Applications for Analytical and Physical Chemistry 2018 Jul 17* (pp. 91-100). Apple Academic Press.
16. GnanaJobitha G, Annadurai G, Kannan C. Green synthesis of silver nanoparticle using *Elettaria cardamomom* and assesment of its antimicrobial activity. *Int. J. Pharma Sci. Res.(IJPSR)*. 2012;3(3):323-30.
17. Ahmad S, Munir S, Zeb N, Ullah A, Khan B, Ali J, Bilal M, Omer M, Alamzeb M, Salman SM, Ali S. Green nanotechnology: A review on green synthesis of silver nanoparticles—An ecofriendly approach. *International journal of nanomedicine*. 2019 Jul 10:5087-107.
18. Khan S, Singh S, Gaikwad S, Nawani N, Junnarkar M, Pawar SV. Optimization of process parameters for the synthesis of silver nanoparticles from Piper betle leaf aqueous extract, and evaluation of their antiphytofungual activity. *Environmental Science and Pollution Research*. 2020 Aug;27:27221-33.
19. Krishnaraj C, Ramachandran R, Mohan K, Kalaichelvan PT. Optimization for rapid synthesis of silver nanoparticles and its effect on phytopathogenic fungi. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2012 Jul 1;93:95-9.
20. Bakar NA, Ismail J, Bakar MA. Synthesis and characterization of silver nanoparticles in natural rubber. *Materials Chemistry and Physics*. 2007 Aug 15;104(2-3):276-83.
21. Ingle Jr, J. D., & Crouch, S. R. (1988). *Spectrochemical analysis*.



22. Kharat SN, Mendhulkar VD. Synthesis, characterization and studies on antioxidant activity of silver nanoparticles using Elephantopus scaber leaf extract. *Materials Science and Engineering: C*. 2016 May 1;62:719-24.
23. Dodge LG. Calibration of the Malvern particle sizer. *Applied optics*. 1984 Jul 15;23(14):2415-9.
24. Havrdova M, Polakova K, Skopalik J, Vujtek M, Mokdad A, Homolkova M, Tucek J, Nebesarova J, Zboril R. Field emission scanning electron microscopy (FE-SEM) as an approach for nanoparticle detection inside cells. *Micron*. 2014 Dec 1;67:149-54.
25. Inkson BJ. Scanning electron microscopy (SEM) and transmission electron microscopy (TEM) for materials characterization. In *Materials characterization using nondestructive evaluation (NDE) methods* 2016 Jan 1 (pp. 17-43). Woodhead publishing.
26. Richardson JT, Scates R, Twigg MV. X-ray diffraction study of nickel oxide reduction by hydrogen. *Applied Catalysis A: General*. 2003 Jun 25;246(1):137-50.